



Associated Technologies  
 694 Higganum Road  
 Durham, CT 06422  
 Phone: (860) 788-3380  
 Fax: (860) 788-3293

## Product Description Sheet

### AT-2010 Structural Acrylic Adhesive

Issued February 22, 2008

#### Description:

Weld Mount AT-2010 is a high performance two part methacrylate adhesive engineered to bond a wide range of plastics, metals and composite assemblies. It offers outstanding bond strength, is extremely durable, with excellent impact and weathering properties. It is a unique adhesive which has very high viscosity to hold Weld Mount parts in position without sagging and it's 5 minute fixture time makes it ideal for production applications. 75% of the ultimate strength is achieved in 15—20 Minutes. Full strength is reached in 24 hours. AT-2010 greatly increases the reliability of finished assemblies with , it's ability to withstand extreme temperature fluctuation and thermal cycling, and resistance to a wide range of chemicals and environmental conditions

#### Physical Properties: (Uncured)

Viscosity @ 25° C (cps)	Resin	85,000—125,000
	Activator	85,000—125,000
Color:	Off White	Light Yellow
Density:		
Mixed Density		
Mixed Ratio:	Volume: 1 to 1	Weight: 1 to 1
Specific Gravity	1.04	
Flashpoint	58° F	

#### Physical Properties: (Cured)

Strength (PSI Steel)	Shear	2,600—3,500
	Tensile	3,800—4,000
Working Time	3 to 4 Minutes	
Handling Strength	20 Minutes For	75% Overall Strength
Gap Fill	0.375 Inches	
Temperature Range::	-65° F - 250° F	
Peak Exotherm	280° F @ 75° F	
	16 Min/10 Grams	

#### Packaging:

AT-2010 is conveniently packaged in 50 ML cartridges. Special packaging is available on request

#### Effects Of Temperature:

AT-2010 is best used at temperatures between 65° F and 80° F. Temperatures below 65° F will slow the cure speed of the material and the viscosities will be higher. Temperatures above 80° F will cause the material to cure faster and the viscosities will be lower. For consistent dispensing maintain temperature as listed above.

#### WHAT AT-2010 BONDS:

##### METALS:

- ALUMINUM
- STEEL
- STAINLESS STEEL
- COATED METALS

##### THERMO SETS:

- FIBERGLASS
- PHENOLICS
- GEL COATS
- EPOXY
- RIM URETHANE
- POLYURETHANE
- LIQUID MOLDING RESINS
- SMC

##### THERMO PLASTICS:

- ACRYLICS
- ABS
- POLYCARBONATES
- NYLONS
- PPO'S
- VINYL'S
- PVC'S
- STYRENE'S
- PEEK'S
- PBT BLENDS
- PET BLENDS

##### BENEFITS:

- ◆ GAP FILLING TO .375"
- ◆ LITTLE SURFACE PREP
- ◆ EXCELLENT STRENGTH
- ◆ IMPACT RESISTANT
- ◆ 100% REACTIVE
- ◆ ROOM TEMPERATURE CURE
- ◆ EASILY APPLIED

# Product Description Sheet

## AT-2010 Structural Acrylic Adhesive

Issued February 22, 2008

### Storage And Shelf Life:

The shelf life of AT-2010 is one year from the date of manufacture which is indicated on the cartridge when refrigerated at 40 degrees F. Shelf life is 6 months from the date of manufacture when the product is stored properly at a temperature no greater than 72° F. Exposure to temperatures above 72 F will reduce the shelf life of the product. AT-2010 should never be frozen.

### Precautions:

AT-2010 is flammable. Keep it away from heat, sparks and open flames.

Keep out of reach of children. This product is for industrial use only. Keep containers closed when not in use. Avoid contact with skin and eyes. Harmful if swallowed. Refer to Material Safety Data Sheet (MSDS) for more complete safety information.

### Mixing:

Mixing: It is highly recommended that either meter mix equipment or cartridges with static mix nozzles be used to properly ratio and dispense the adhesive. For hand mixing, combine Part A and Part B in the correct ratio and mix thoroughly. Heat buildup during and after mixing is normal. To reduce the likelihood of exothermic reaction or excessive heat buildup, mix less than 100 grams at a time. Mixing smaller amounts will minimize heat buildup.

### Bonding:

For optimum bond strength and to insure maximum performance in the finished assembly mate parts together within the specified working time of the adhesive (3—4 Minutes). Make sure the bond joint has uniform coverage and that a sufficient amount of adhesive is in the bond area. It is important to have the adhesive applied, parts aligned and positioned, within the established work time for the product. To ensure maximum performance in the finished assembly parts should remain undisturbed until the joint is sufficiently cured.

For the highest strength bonds surfaces should be clean, dry, and free of contamination. Extensive surface preparation is not required for AT-2010 and good bonds can be formed on most substrates after a solvent wipe. However we recommend that metal surfaces (particularly aluminum) be given a scotchbrite cleaning to remove surface oxidation to achieve the highest bond strengths.

### Clean Up:

It is important to remove excess adhesive from the substrate before it is cured. Solvent cleaners such as alcohol or MEK yield good results. Once the adhesive has cured it will be very difficult to remove and may require as much as 350° F to soften to allow removal.

### Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Associated Technologies specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Associated Technologies products. Associated Technologies specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide.